# Outershield® 71E-H

## **TOP FEATURES**

- Rutile flux cored wire for high quality welding with M21 gas
- Excellent operator appeal due to superior welding characteristics
- Superior product consistency with optimal alloy control
- H4 class in 1.6mm diameter
- Full out-of-position capability with high deposition rates

#### **CLASSIFICATION**

AWS A5.20 E71T-1M-J / E71T-1C-H4
EN ISO 17632-A T 46 3 P M 1 H5 / T 42 0 P C 1 H5

#### **CURRENT TYPE**

DC+

## **WELDING POSITIONS**

ΔI

## **SHIELDING GASES (ACC. ISO 14175)**

M21 Mixed gas Ar+ (>15-25%) CO2 C1 Active gas 100% CO2

Flow rate 15-25 I/min

#### **APPROVALS**

ABS	LR	BV	DNV/GL	RINA	RMRS
+	+	+	+	+	+

# **CHEMICAL COMPOSITION (WEIGHT %), TYPICAL, ALL WELD METAL**

Shielding gas	С	Mn	Si	Р	S	НДМ
M21	0.04	1.4	0.6	0.013	0.010	3 ml/100 g
C1	0.05	1.3	0.6	0.015	0.010	3 ml/100 g

# **MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL**

	Shielding	Condition*	Yield strength	Tensile strength	Elongation (%)	Elongation Impact ISO-V (J)			)
	gas	Condition	(MPa)	(MPa)		0°C	-20°C	-30°C	-40°C
Required: AWS A5.20			min. 400	min. 480	min. 22				min. 27
EN ISO 17632-A			min. 460	530-680	min. 20			min. 47	
Typical values	M21	AW	570	620	25		90	65	40
	C1	AW	520	575	24	80			

<sup>\*</sup> AW = As welded

# **PACKAGING AND AVAILABLE SIZES**

Wire diameter (mm)	Packaging	Weight (kg)	Item number			
1.2	SPOOL (S200) SPOOL (B300) SPOOL (S300) DRUM	5.0 16.0 16.0 200.0	900125 900118N, 900156N 900149N, 900149NE 900297			
1.6	SPOOL (S300)	16.0	900262N, 900262NE			

Outershield® 71E-H-EN-01/07/22



#### **TEST RESULTS**

Test results for mechanical properties, deposit or electrode composition and diffusible hydrogen levels were obtained from a weld produced and tested according to prescribed standards, and should not be assumed to be the expected results in a particular application or weldment. Actual results will vary depending on many factors, including, but not limited to, weld procedure, plate chemistry and temperature, weldment design and fabrication methods. Users are cautioned to confirm by qualification testing, or other appropriate means, the suitability of any welding consumable and procedure before use in the intended application

Safety Data Sheets (SDS) are available here:



Subject to Change – The information is accurate to the best of our knowledge at the time of printing. Please refer to <a href="www.lincolnelectric.eu">www.lincolnelectric.eu</a> for any updated information.

Outershield® 71E-H-EN-01/07/22

